

# polyethylene

## SCLAIR® FP112-A Resin

Octene Copolymer VLDPE Film Resin



product data sheet

Property	ASTM <sup>(1)</sup>	Typical Values <sup>(2)</sup>
Melt Index <sup>(3)</sup>	D 1238	0.9 g/10 min
Density	D 792	0.912 g/cm <sup>3</sup>
	METRIC UNITS	ENGLISH UNITS

**Melt Index** 0.9

**Density** 0.912

**Slip** None

**Antiblock** None

### Film Properties <sup>(4)</sup>

Thickness		51 µm	2.0 mil
Tear Strength	MD D 1922	710 g	
	TD	1,010 g	
Dart Drop Impact, F <sub>50</sub>	D 1709/A	>1 000 g	
Low Friction Puncture <sup>(5)</sup>		62 J/mm	14 in-lb/mil
Tensile Strength	MD D 882	49 MPa	7,100 psi
	TD	54 MPa	7,800 psi
Yield Strength	MD D 882	7 MPa	1,100 psi
	TD	7 MPa	1,100 psi
Elongation	MD D 882	640 %	640 %
	TD	890 %	890 %
1% Secant Modulus	MD D 882	114 MPa	16,500 psi
	TD	123 MPa	17,800 psi
Haze	D 1003	8.7 %	8.7 %
Gloss @ 45°	D 2457	63	63

### Features

- Low seal initiation temperature
- High toughness
- Very good optical properties
- Low gel

### Additives

- Processing antioxidant

### Applications

- Sealant and lamination film for food packaging

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/2.16 kg.

(4) Film properties are typical of blown film extruded on a 2.5" extruder with 4" die and 100-mil die gap at a blow up ratio of 2.5:1, but are dependent upon operating conditions.

(5) NOVA Chemicals test method.

## PRODUCT DATA SHEET

# SCLAIR FP112-A Resin

## Octene Copolymer VLDPE Film Resin

### Availability

SCLAIR FP112-A polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

### Storage/Handling

SCLAIR FP112-A resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Material Safety Data Sheet (MSDS) contains important safety information and should be reviewed before using the product.

### Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

### Food Packaging Status

United States: SCLAIR FP112-A resin complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 3.2a, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without temperature or food-type restrictions, subject to technical suitability.

Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

### Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



4 is the SPI resin code developed for low density and linear low density polyethylene to identify material type for sorting and recycling purposes.

 is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.

SCLAIR® is a registered trademark of NOVA Chemicals Corporation in Canada and of NOVA Chemicals (International) S.A. elsewhere; authorized use/utilisation autorisée.

August 12, 2013